



Innovation and Experience at Work

## EvoLube TEK616

This evolutionary polyurea-thickened grease has outstanding long-life properties. Polyurea thickeners act to inhibit oxidation thereby adding to the long-life effectiveness of this grease. EvoLube TEK616 contains a very light viscosity white mineral oil that gives it excellent low temperature properties at -43°C. It can also operate at temperatures up to +205°C. It is a shear stable, multipurpose, water resistant grease and is compatible with most plastics and seals. There are no heavy metals, which makes it environmentally friendly.

BASE OIL CHARACTERISTICS			TYPICAL VALUE *
Туре			Mineral Oil
Temperature Service Range (°C)			-43 to 205
GREASE CHARACTERISTICS			TYPICAL VALUE *
Thickener			Polyurea
Color			Blue
Appearance			Smooth
NLGI Grade			2
Penetration (ASTM D217 / DIN 51804-T1)	Unworked		265-295
	Worked	60X	265-295
Dropping Point (°C) (ASTM D2265 / DIN ISO 2176)			260 min.
Oil Separation (ASTM D1742)	24h at 25°C and 1.72 kPa		0.24%
Evaporation (CTM-1)	24h at 100°C		1.58%
Water Washout (ASTM D1264 / DIN 51807-T2)	60 min at 38°C		3.92%
Copper Corrosion (ASTM D130 / DIN 51811)	24h at 100°C		1a
Four Ball Wear (ASTM D2266 / DIN 51350-T5)	60 min 1200 RPM 75°C 40kg <sub>f</sub>		0.52mm
	Dynamic Coefficient of Friction (steel on steel)		0.086
Specific Gravity (CTM-2)	25°C		0.972
Low Temperature Torque (ASTM D1478)	-40°C	Start	3,153 g-cm (0.309 N-m)
		Run 10 min	1,788 g-cm (0.175 N-m)
		Run 60 min	455 g-cm (0.044 N-m)

\*The values stated in this Product Data Sheet are Typical Values and *must not* be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.

## **Engineered Custom Lubricants**

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: eclusa\_customer@quakerhoughton.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.