

CHRISTO-LUBE® MCG 129

CHRISTO-LUBE® MCG 129 is a fully fluorinated grease thickened with PTFE which operates under extreme temperature conditions, has outstanding stability with oxygen and excellent compatibility with metals, plastics and elastomers. This medium consistency fluorinated lubricant is particularly useful in lubricating valve and regulator components found in medical and industrial gas applications. CHRISTO-LUBE® MCG 129 is registered with NSF as a H1 lubricant meaning it is acceptable for use in or around food processing equipment. It is designed for use in all food processing operations including mixing, stirring, baking, frying, cooking, freezing, cleansing, packaging, canning and bottling. In addition, this grease is formulated with rust preventative additives for protection of metal parts which are subject to corrosion



This product is registered H1 by the NSF (135039)

BASE OIL CHARACTERISTICS		TYPICAL VALUE *
Type		PFPE
Temperature Service Range (°C)		-30 to 175
Flash Point (°C) (ASTM D92)		None
GREASE CHARACTERISTICS		
Thickener		PTFE
Color		White
Appearance		Smooth
NLGI Grade		2
Penetration (ASTM D217 / DIN 51804-T1)	Unworked	265-295
	Worked	60X 265-295
Oil Separation (ASTM D6184)	24h at 149°C	10% max.
Evaporation (CTM-1)	24h at 149°C	3% max.
Water Washout (ASTM D1264 / DIN 51807-T2)	60 min at 79°C	0%
Four Ball Wear (ASTM D2266 / DIN 51350-T5)	60 min 1200 RPM 75°C 40kg _f	0.562mm
	Dynamic Coefficient of Friction (steel on steel)	0.105
Specific Gravity (CTM-2)	25°C	1.979

*The values stated in this Product Data Sheet are Typical Values and **must not** be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.

Engineered Custom Lubricants

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: eclusa_customer@quakerhoughton.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.