

Product Data Sheet

Innovation and Experience at Work

RheoGel 1605

RheoGel 1605 is a low temperature capable synthetic grease thickened with PTFE. It offers very smooth, low noise and low friction performance at high and low temperatures with great water resistance and very good surface adhesion. This makes is a perfect track grease for sunroofs, window lift actuators and seats and many other automotive components.

| BASE OIL CHARACTERISTICS | | | TYPICAL VALUE * |
|---|--|-----|--------------------------|
| Туре | | | Synthetic Hydrocarbon |
| Temperature Service Range (°C) | | | -40 to 120 |
| GREASE CHARACTERISTICS | | | TYPICAL VALUE * |
| Thickener | | | PTFE |
| Color | | | White |
| Appearance | | | Smooth |
| NLGI Grade | | | 1.5 |
| Penetration (ASTM D217 / DIN 51804-T1) | Unworked | | 285-315 |
| | Worked | 60X | 285-315 |
| Dropping Point (°C) (ASTM D2265 / DIN ISO 2176) | | | 260 min. |
| Oil Separation (ASTM D6184) | 24h at 100°C | | 5% max. |
| Evaporation (CTM-1) | 24h at 100°C | | 2% max. |
| Water Washout (ASTM D1264 / DIN 51807-T2) | 60 min at 38°C | | 1.0% |
| Four Ball Wear (ASTM D2266 / DIN 51350-T5) | 60 min 1200 RPM 75°C 40kg _f | | 0.50mm |
| | Dynamic Coefficient of Friction (steel on steel) | | 0.079 |
| Specific Gravity (CTM-2) | 25°C | | 1.2 |

^{*}The values stated in this Product Data Sheet are Typical Values and *must not* be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.