



Innovation and Experience at Work

RheoGel 1930

RheoGel 1930 is a soft, low viscosity, synthetic electrical switch contact grease that is ideally suited to low force switch contacts. Ideal for low to medium current switches that require optimal performance at low temperatures.

| BASE OIL CHARACTERISTICS | | | TYPICAL VALUE * |
|---|--------------|-----|--------------------------|
| Туре | | | Synthetic Hydrocarbon |
| Temperature Service Range (°C) | | | -40 to 150 |
| GREASE CHARACTERISTICS | | | TYPICAL VALUE * |
| Thickener | | | Lithium |
| Color | | | Off White |
| Appearance | | | Smooth |
| NLGI Grade | | | 0.5 |
| Penetration (ASTM D217 / DIN 51804-T1) | Unworked | | 330-360 |
| | Worked | 60X | 330-360 |
| Dropping Point (°C) (ASTM D2265 / DIN ISO 2176) | | | 200 min. |
| Oil Separation (ASTM D6184) | 24h at 100°C | | 10% max. |
| Evaporation (CTM-1) | 24h at 100°C | | 2% max. |

*The values stated in this Product Data Sheet are Typical Values and *must not* be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.

Engineered Custom Lubricants

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: eclusa_customer@quakerhoughton.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.