



Innovation and Experience at Work

TriboGel 752

TriboGel 752 is a fully synthetic polyurea thickened grease with a polymer additive. This grease provides moderate dampening, good EP/anti-wear capability, and excellent water resistance. Applications include small gears and automotive recliners. TriboGel 752 is also resistant to degradation from high temperature welding and washout during autophoretic coating processes.

BASE OIL CHARACTERISTICS			TYPICAL VALUE *
Туре			Synthetic Hydrocarbon
Temperature Service Range (°C)			-40 to 125
GREASE CHARACTERISTICS			TYPICAL VALUE *
Thickener			Polyurea
Color			Off White
Appearance			Smooth
NLGI Grade			1.5
Penetration (ASTM D217 / DIN 51804-T1)	Unworked		295
	Worked	60X	291
Dropping Point (°C) (ASTM D2265 / DIN ISO 2176)			260 min.
Oil Separation (ASTM D6184)	24h at 100°C		0.11%
Evaporation (CTM-1)	24h at 100°C		0.14%
Specific Gravity (CTM-2)	25°C		0.88
Apparent Viscosity (Brookfield Viscometer T-C spindle, 1 rpm)	-40°C		5,900,000 cP
Four Ball Wear (ASTM D2266 / DIN 51350-T5)	60 min 1200 RPM 75°C 40kg _f		0.59mm
Oxidation Stability (ASTM D942 / DIN 51808)	100h at 100°C		3.5 kPa

*The values stated in this Product Data Sheet are Typical Values and *must not* be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.

Engineered Custom Lubricants

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: eclusa_customer@quakerhoughton.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.