



Innovation and Experience at Work

ViscoTech R174

ViscoTech R174 is a lithium-based grease utilizing very light viscosity mineral oil and PTFE. Because of the outstanding aniline point of the base oil, this material offers excellent compatibility with most polymer and elastomer materials. The low temperature characteristics of the material will give superior low torque start up. It also provides oxidation resistance over a wide temperature range and is water resistant.

BASE OIL CHARACTERISTICS				TYPICAL VALUE *
Туре				Mineral Oil
Temperature Service Range (°C)				-40 to 100
Aniline Point (°C) (ASTM D611)				98
GREASE CHARACTERISTICS				TYPICAL VALUE *
Thickener			Lithium	
Color				Off White
Appearance			Smooth	
NLGI Grade				1
Penetration (ASTM D217 / DIN 51804-T1)	Worked		60X	310-340
Dropping Point (°C) (ASTM D2265 / DIN ISO 2176)				170 min.
Oil Separation (ASTM D6184)	24h at 100°C			15% max.
Oil Separation (ASTM D1742)	24h at 25°C and 1.72 kPa			16 %
Evaporation (CTM-1)	24 at 100°C		5% max.	
Four Ball Wear (ASTM D2266 / DIN 51350-T5)	60 min 1200 RPM 75°C 40kg _f		0.61mm	
Specific Gravity (CTM-2)	25°C		1.016	
Oxidation Stability (ASTM D942 / DIN 51808)	100h at 100°C		14 kPa	
	1000h at 100°C	1000h at 100°C		
Apparent Viscosity (Brookfield Viscometer T-C spindle, 1 rpm)	-40°C		2,690,000 cP	
Low Temperature Torque (ASTM D1478)	-40°C	S	tart	1,736 g-cm
	-40 0		0 min.	293 g-cm

*The values stated in this Product Data Sheet are Typical Values and *must not* be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.

Engineered Custom Lubricants

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: eclusa_customer@quakerhoughton.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.