

CHRISTO-LUBE® MCG 153

CHRISTO-LUBE® MCG 153 is a fully fluorinated grease thickened with PTFE which operates under extreme temperature conditions, has outstanding stability with oxygen and excellent compatibility with metals, plastics and elastomers. This medium consistency fluorinated lubricant is especially useful in lubricating valve and regulator components where non-reactivity with harsh chemicals, fuels and solvents is an important factor. Additionally, CHRISTO-LUBE® MCG 153 is used to lubricate plastic components typically found in automotive applications and is approved to Chrysler Material Specification MS-9987 and meets Ford Material specification WSS-M13P12-A.



This product is registered H1 by the NSF (156997)

BASE OIL CHARACTERISTICS		TYPICAL VALUE *
Type		PFPE
Temperature Service Range (°C)		-30 to 260
Flash Point (°C) (ASTM D92)		None
GREASE CHARACTERISTICS		
Thickener		PTFE
Color		White
Appearance		Smooth
NLGI Grade		2
Penetration (ASTM D217 / DIN 51804-T1)	Unworked	265-295
	Worked	60X 265-295
Oil Separation (ASTM D6184)	24h at 149°C	7% max.
Evaporation (CTM-1)	24h at 149°C	3% max.
Evaporation (CTM-1)	24h at 177°C	0.15%
Water Washout (ASTM D1264 / DIN 51807-T2)	60 min at 79°C	0.35%
Four Ball Wear (ASTM D2266 / DIN 51350-T5)	60 min 1200 RPM 75°C 40kg _f	0.783mm
	Dynamic Coefficient of Friction (steel on steel)	0.08
Specific Gravity (CTM-2)	25°C	1.99

*The values stated in this Product Data Sheet are Typical Values and **must not** be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.

Engineered Custom Lubricants

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: eclusa_customer@quakerhoughton.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.