

Absolube 5111A

Absolube 5111A is Absolube 411A cut with non-combustible fluorinated solvent. When this material is applied, the solvent evaporates and leaves behind a film of Absolube 411A. An ultraviolet dye is dispersed in this material to make the residual film of Absolube 411A more visible. Details of Absolube 411A are included below:

The base grease Absolube 411A is synthetic grease made from polyfluoropolyether (PFPE) fluid thickened with polytetrafluoroethylene (PTFE) polymer. This grease has excellent low temperature properties and is inert to oxygen and other aggressive chemicals. The PFPE fluid has extremely low surface tension and this gives Absolube 411A the ability to work in applications where other lubricants fail due to lubricant starvation. The fully fluorinated chemistry is completely compatible with a vast majority of plastics and elastomers.

BASE OIL CHARACTERISTICS		TYPICAL VALUE *
Type		PFPE
Temperature Service Range (°C)		-60 to 200
Flash Point (°C) (ASTM D92)		None
GREASE CHARACTERISTICS		TYPICAL VALUE *
Thickener		PTFE
Color		White
Appearance		Smooth
NLGI Grade		2
Penetration (ASTM D217 / DIN 51804-T1)	Unworked	250 min.
		60X 265-295
	Worked	10,000X 261
		100,000X 249
Dropping Point (°C) (ASTM D2265 / DIN ISO 2176)		260 min.
Oil Separation (ASTM D6184)	24h at 100°C	10% max.
Evaporation (CTM-1)	24h at 100°C	3% max.
Water Washout (ASTM D1264 / DIN 51807-T2)	60 min at 79°C	0.14%
Copper Corrosion (ASTM D130 / DIN 51811)	24h at 100°C	1b max.
Apparent Viscosity (Brookfield Viscometer T-C spindle, 1 rpm)	-40°C	2,260,000 cP
Four Ball Wear (ASTM D2266 / DIN 51350-T5)	60 min 1200 RPM 75°C 40kg _f	0.78mm
Specific Gravity (CTM-2)	25°C	1.96
Oxidation Stability (ASTM D942 / DIN 51808)	168h at 100°C	0 kPa
Low Temperature Torque (ASTM D1478)	-40°C	Start 449 g-cm
		Run 10 min 332 g-cm
		Run 60 min 319 g-cm

*The values stated in this Product Data Sheet are Typical Values and **must not** be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.



A QUAKER HOUGHTON COMPANY

Innovation and Experience at Work

Product Data Sheet

Engineered Custom Lubricants

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: eclusa_customer@quakerhoughton.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.