




A QUAKER CHEMICAL COMPANY

Innovation and Experience at Work



CHRISTO-LUBE[®] MCG 183

BASE OIL CHARACTERISTICS		TYPICAL VALUE *
Type		PFPE
Temperature Service Range (°C)		-50 to 300
Flash Point (°C) (ASTM D92)		None
GREASE CHARACTERISTICS		
Thickener		Boron Nitride
Color		White
Appearance		Smooth
NLGI Grade		2
Penetration (ASTM D217 / DIN 51804-T1)	Unworked	265-295
	Worked	60X 265-295
Dropping Point (°C) (ASTM D2265 / DIN ISO 2176)		260 min.
Oil Separation (ASTM D6184)	24h at 149°C	10% max.
Evaporation (CTM-1)	24h at 149°C	3% max.
Copper Corrosion (ASTM D130 / DIN 51811)	24h at 100°C	1a

Engineered Custom Lubricants

ISO/TS16949:2009 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: customerservice@ecllube.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications. ECLI Products, LLC, owns and does business as Engineered Custom Lubricants and Lubrication Technology.