

## TriboGel 206

TriboGel 206 is a synthetic hydrocarbon grease prepared from a lithium-based thickening agent and fortified with additives to improve oxidative stability.

BASE OIL CHARACTERISTICS		TYPICAL VALUE *	
Type		Synthetic Hydrocarbon	
Temperature Service Range (°C)		-40 to 125	
GREASE CHARACTERISTICS		TYPICAL VALUE *	
Thickener		Lithium	
Color		White	
Appearance		Smooth	
NLGI Grade		1 to 1.5	
Penetration (ASTM D217 / DIN 51804-T1)	Unworked	290-320	
	Worked	60X	290-320
		100,000X	301
Dropping Point (°C) (ASTM D2265 / DIN ISO 2176)		180 min.	
Oil Separation (ASTM D6184)	24h at 100°C	3% max.	
Evaporation (CTM-1)	24h at 100°C	1% max.	
Water Washout (ASTM D1264 / DIN 51807-T2)	60min at 38°C	1.5%	
Water Washout (ASTM D1264 / DIN 51807-T2)	60min at 79°C	2.48%	
Copper Corrosion (ASTM D130 / DIN 51811)	24h at 100°C	1b	
Salt Spray Corrosion (ASTM B117)	100h at 35°C	Pass	
Apparent Viscosity (Brookfield Viscometer T-C spindle 1 rpm)	-40°C	5.7 x 10 <sup>6</sup> cP	
Four Ball Wear (ASTM D2266 / DIN 51350-T5)	60min 1200rpm 75°C 40kg <sub>r</sub>	0.52mm	
Specific Gravity (CTM-2)		0.87 g/cm <sup>3</sup>	
Four Ball Weld (ASTM D2596 / DIN 51350-T4)	Last Non-seizure (scar)	80 kg (0.41mm)	
	Last Seizure (scar)	200 kg (2.99 mm)	
	Weld Load	250 kg	
Oxidation Stability (ASTM D942 / DIN 51808)	168h at 100°C	6.9 kPa	
Low Temperature Torque (ASTM D1478)	-30°C	Start	1125 g-cm
		Run 10 min	416 g-cm
		Run 60 min	397 g-cm
Low Temperature Torque (ASTM D1478)	-40°C	Start	2,191 g-cm
		Run 10 min	943 g-cm
		Run 60 min	657 g-cm

\*The values stated in this Product Data Sheet are Typical Values and **must not** be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.

### Engineered Custom Lubricants

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: [eclusa\\_customer@quakerhoughton.com](mailto:eclusa_customer@quakerhoughton.com) • [www.eclube.com](http://www.eclube.com)

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.