



Innovation and Experience at Work

CHRISTO-LUBE® MCG 146

CHRISTO-LUBE® MCG 146 is a fully fluorinated grease thickened with PTFE which operates under extreme temperature conditions, has outstanding stability with oxygen and excellent compatibility with metals, plastics and elastomers. This soft fluorinated lubricant is especially useful in lubricating bearings, gears, splines and actuators at low temperatures where extremely low torque is an important factor. CHRISTO-LUBE® MCG 146 is formulated with corrosion inhibitors for protection of lubricated parts in long term storage and is also registered with NSF as an H-1 lubricant meaning it is acceptable for us in or around food processing equipment. It is designed for use in all food processing operations including mixing, stirring, baking, frying, cooking, freezing, cleansing, packaging, canning and bottling.



This product is registered H1 by the NSF (147196)

BASE OIL CHARACTERISTICS			TYPICAL VALUE *
Туре			PFPE
Temperature Service Range (°C)			-70 to 150
Flash Point (°C) (ASTM D92)			None
GREASE CHARACTERISTICS			
Thickener			PTFE
Color			White
Appearance			Smooth
NLGI Grade			2
Penetration (ASTM D217 / DIN 51804-T1)	Unworked		275-295
	Worked	60X	275-295
Oil Separation (ASTM D6184)	24h at 149°C		10% max.
Evaporation (CTM-1)	24h at 149°C		3% max.
Water Washout (ASTM D1264 / DIN 51807-T2)	60 min at 79°C		0%
Four Ball Wear (ASTM D2266 / DIN 51350-T5)	60 min 1200 RPM 75°C 40kg _f		0.492mm
	Dynamic Coefficient of Friction (steel on steel)		0.094
Specific Gravity (CTM-2)	25°C		1.894

*The values stated in this Product Data Sheet are Typical Values and *must not* be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.

Engineered Custom Lubricants

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: eclusa_customer@quakerhoughton.com • <u>www.ecllube.com</u>

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.