



Innovation and Experience at Work

CHRISTO-LUBE® MCG 195

CHRISTO-LUBE® MCG 195 is a fully fluorinated grease thickened with PTFE which operates under extreme temperature conditions, has outstanding stability with oxygen and excellent compatibility with metals, plastics and elastomers. This soft consistency fluorinated lubricant is especially useful in lubricating under-hood automotive components where high temperature stability and non-reactivity with chemicals and fuels are important factors.

| BASE OIL CHARACTERISTICS | | | TYPICAL VALUE * |
|---|--------------|-----|-----------------|
| Туре | | | PFPE |
| Temperature Service Range (°C) | | | -25 to 260 |
| Flash Point (°C) (ASTM D92) | | | None |
| GREASE CHARACTERISTICS | | | TYPICAL VALUE * |
| Thickener | | | PTFE |
| Color | | | White |
| Appearance | | | Smooth |
| NLGI Grade | | | 0.5 |
| Penetration (ASTM D217 / DIN 51804-T1) | Unworked | | 330-360 |
| | Worked | 60X | 330-360 |
| Dropping Point (°C) (ASTM D2265 / DIN ISO 2176) | | | 200 min. |
| Oil Separation (ASTM D6184) | 24h at 149°C | | 10% max. |
| Evaporation (CTM-1) | 24 at 149°C | | 3% max. |

*The values stated in this Product Data Sheet are Typical Values and *must not* be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.

Engineered Custom Lubricants

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: eclusa_customer@quakerhoughton.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.