

RheoGel 916A

RheoGel 916A is an excellent low temperature, polymer fortified synthetic grease approved to the VW TL 778-B specification. It is useful for many body hardware, latch and seat applications. It is also a very good multipurpose low temperature lubricant. This product is fortified with polytetrafluoroethylene.

BASE OIL CHARACTERISTICS		TYPICAL VALUE *	
Type		Synthetic Hydrocarbon	
Temperature Service Range (°C)		-40 to 125	
GREASE CHARACTERISTICS		TYPICAL VALUE *	
Thickener		Lithium	
Color		Off White	
Appearance		Smooth	
NLGI Grade		2	
Penetration (ASTM D217 / DIN 51804-T1)	Unworked	265-295	
	Worked	60X	265-295
		100,000X	347
		100,000X Change	29%
Dropping Point (°C) (ASTM D2265 / DIN ISO 2176)		185 min.	
Oil Separation (ASTM D6184)	24h at 100°C	6% max.	
Oil Separation (DIN 51 817)	168h at 40°C	5.5%	
Evaporation (CTM-1)	24h at 100°C	1% max.	
Copper Corrosion (ASTM D130 / DIN 51811)	24h at 100°C	1b	
Four Ball Wear (ASTM D2266 / DIN 51350-T5)	60 min 1200 RPM 75°C 40kg _r	0.43mm	
	Dynamic Coefficient of Friction (steel on steel)	0.071	
EMCOR (ASTM D6138/DIN 51 802)		0	
Oxidation Stability (ASTM D942 / DIN 51808)	100h at 100°C	2 kPa	
	168h at 100°C	16 kPa	
Kesternich Flow Pressure (DIN 51 805)	20°C	10.2 kPa	
	-35°C	29.2 kPa	
Specific Gravity (CTM-2)	25°C	0.91	
Apparent Viscosity (Brookfield Viscometer T-C spindle, 1 rpm)	-40°C	1,048,000 cP	
Low Temperature Torque (ASTM D1478)	-40°C	Start	839 g-cm
		Run 60 min	241 g-cm

*The values stated in this Product Data Sheet are Typical Values and **must not** be used as QC Specifications for this product. Please contact the Global Technical Services department for QC specifications for this product.

Engineered Custom Lubricants

IATF 16949 • Registered QMS

3851 Exchange Ave. • Aurora, IL 60504 • T: 630.449.5000 • F: 630.585.0050 • E: eclusa_customer@quakerhoughton.com • www.ecllube.com

DISCLAIMER: Since we cannot anticipate or control the many different conditions under which this information and our product may be used, we cannot guarantee the applicability of this information or the suitability of our product in any individual situation. For the same reason, the product discussed is sold without warranty expressed or implied. Please contact Engineered Custom Lubricants for assistance and recommendations prior to writing or releasing any engineering specifications.